

Article No.	1777
EAN-Code	4251744517774
Title	Eur. Oak FJ B/C 20x4200x1250
Thickness in mm	20
Length in mm	4200
Width in mm	1250
Type of wood	Eiche
Quality	B/C ohne Äste
Type of lamella	kgz
Width of lamella	ca. 40-50mm fix
Packaging / Foiling	
Description	Solid wood panel, Europ. Oak, Quality B/C (topside B max. 20% sound sap, single pin knots permitted / Bottomside sap without limit, small knots filled in wood color), FJ fingerjointed, lamella widths ca. 40-45mm fix, glued D4-EN 204, sanded 100 grit, bulk foiled, size 20x4200x1250mm
Wood moisture	At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity
Gluing	All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.
DIN standard	All LARBON® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).