

<b>Article No.</b>	1988
<b>EAN-Code</b>	4251744519884
<b>Title</b>	europ.walnut,FJ fingerjointed,Rustic/C,
<b>Thickness in mm</b>	30
<b>Length in mm</b>	5000
<b>Width in mm</b>	1255
<b>Type of wood</b>	Nussbaum eur. ged. Küpla
<b>Quality</b>	Rustik A/C
<b>Type of lamella</b>	kgz
<b>Width of lamella</b>	ca. 39-43mm fix
<b>Packaging / Foiling</b>	paketw. 5 Stk/Paket
<b>Description</b>	eur. walnut lightly steamed,solid wood panel, FJ fingerjointed, quality Rustic,width of lamella 40 mm fix,bulked foiled,glued D3-DIN/EN 204,sanded 100 grit,dimension 30 mm x 5000 mm x 1255 mm
<b>Wood moisture</b>	At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity
<b>Gluing</b>	All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.
<b>DIN standard</b>	All LARBON <sup>®</sup> solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).