

RECIN Product Datasheet

| Article No. | 1999 |
|---------------------|--|
| EAN-Code | 4251744519990 |
| Title | Oak Live Edge table EGP Rustic 40x2000x1000 foiled |
| Thickness in mm | 760 |
| Length in mm | 2200 |
| Width in mm | 1000 |
| Type of wood | Tisch Akazie Baumkante |
| Quality | Akazie |
| Type of lamella | DL Baumkante |
| Width of lamella | Platte: 55mm (25+30) fallend |
| Packaging / Foiling | im Karton |
| Description | Solid wood panel for table top, Europ. Oak, real "Live Edge", Quality RUSTIC |
| | (topside Rustik, no sap / sap only on bottom side C, both sides knots filled black, |
| | EGP long lamella, random widths of lamella, m.c. 8+/-2%, glued D4-EN 204, |
| | sanded 100 grit, FSC 100%, single foiled, size 40x2000x1000mm |
| Wood moisture | At the end of production, the wood moisture is approx. 8 +/- 2%, which |
| | corresponds to the equilibrium moisture when used in closed rooms with a |
| | healthy living climate of 20°C / 55% humidity |
| Gluing | All solid wood panels / glued wood panels are glued formaldehyde-free using |
| | tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in |
| | accordance with DIN/EN 204. Areas of application for these PVAc glues (=white |
| | glues) are indoor areas with frequent short-term exposure to runoff water or |
| | condensation and/or exposure to high humidity. As well as outdoor areas, but |
| | protected from the weather. The glue content for solid wood panels is only |
| | approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, |
| | chipboards are usually bound to formaldehyde resin and have a glue content of |
| | up to 10%). With D3 gluing, only the technical class of solid wood panels |
| | according to EN 13353 of SWP/1 (dry area according to EN 13986) can be |
| | achieved. With D4 gluing, only the technical class of solid wood panels according |
| | to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved. |
| DIN standard | All LARBON [®] solid wood panels clearly exceed the necessary specifications of the |
| | European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 |
| | (optical appearance classes). |