

Article No.	2531				
EAN-Code	4251744525311				
Title	Oak FJ 27x2500x1240mm C/C for veneering				
Thickness in mm	27				
Length in mm	2500				
Width in mm					
Type of wood	1240				
Quality	Eiche zum furnieren				
	C/C zum furnieren				
Type of lamella Width of lamella	kgz Lamelle fix				
	Lamene nx				
Packaging / Foiling	Calid was allowed Suren California inted CIC few concerns advanciable				
Description	Solid wood panels, Europ. Oak, fingerjointed, C/C for veneering, edges visible,				
	bulk foiled, Exact thickness - Tolerance thickness +/-0,2mm – proper calibration,				
	Cut to size -0mm/+max. 2mm				
	Widths of lamella of no interest – but only one widths in same panel				
	Sap both sides of no interest (but on the long edge (= the first and the last				
	lamella) not full of sap on edges				
	Knots of no interest, but flat closed surface (will get veneered) and no knots on				
	edges (edges visible)				
	Filler permitted (flat closed surface)				
	color of no interest (closed surface)				
	Yellow fungi permitted – but not visible on edges				
	only single Worm Holes by accident				
NA/o o d we distring	Sanding 80 or 100 grit, size 27x2500x1240mm				
Wood moisture	At the end of production, the wood moisture is approx. 8 +/- 2%, which				
	corresponds to the equilibrium moisture when used in closed rooms with a				
Chrise	healthy living climate of 20°C / 55% humidity				
Gluing	All solid wood panels / glued wood panels are glued formaldehyde-free using				
	tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white				
	glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but				
	protected from the weather. The glue content for solid wood panels is only				
	approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of				
	up to 10%). With D3 gluing, only the technical class of solid wood panels				
	according to EN 13353 of SWP/1 (dry area according to EN 13986) can be				
	achieved. With D4 gluing, only the technical class of solid wood panels according				
DIN standard	to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.				
DIN standard	All LARBON® solid wood panels clearly exceed the necessary specifications of the				
	European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2				
	(optical appearance classes).				