

| Article No. | 2616 |
|---------------------|---|
| EAN-Code | 4251744526165 |
| Title | Ash Live Edge table EGP Rustic 40x2000x900 foiled |
| Thickness in mm | 40 |
| Length in mm | 2000 |
| Width in mm | 900 |
| Type of wood | Esche Kern Tischplatte Baumkante |
| Quality | Kernesche astig |
| Type of lamella | DL echte Baumkante |
| Width of lamella | ca. 40-100mm fallend |
| Packaging / Foiling | einzeln foliert |
| Description | Solid wood panel for table top, Europ. Ash, natural "Live Edge", Quality RUSTIC (knots permitted, brownheart permitted, not color sorted, knots fillered in wood color), EGP long lamella, random widths of lamella ca. 40-100mm, m.c. 8+/-2%, glued D3-EN 204, sanded 100 grit, not oiled, single foiled, leaflet under foil, FSC 100%, size 40x2000x900mm |
| Wood moisture | At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity |
| Gluing | All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved. |
| DIN standard | All LARBON ® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes). |